



## Enclosure size



## Core size



A	23.5±1.0mm
B	22.2±1.0mm
C	13.5±0.8mm
D	36.0±1.0mm
E	10.5±1.0mm
F	20±1.0mm
G	29.4±1.0mm
H	13±0.8mm

Material: Nickel-zinc ferrite  
Initial Permeability:  $850 \pm 20\%$

Initial Permeability :  $850 \pm 20\%$

Relative Loss Factor: 16 (0.1MHz)\*10<sup>(-6)</sup>

Relative Temperature Coefficient:  $5 - 10 \cdot 10^{-6}$



Saturation Magnetic Flux Density: 280(1600A/m)MT


Remanence: 200mT

Coercivity: 20A/m

Curie Temperature:  $>130^{\circ}\text{C}$



Electrical Resistivity:  $>10^{(5)}\Omega^*m$

	
<b>Title:</b> Ferriti Core / Ferriti Ring for round cable 13 mm 2 pieces black	
<b>Dat</b>	2024 / 07 / 19
<b>Unit</b>	mm
<b>Projection</b>	
<b>Rev</b>	A
<b>Item no.</b>	80948
<b>Barcode</b>	4043619809486
<b>File No.</b>	88417

[illegible]

$\Phi_C$  (Core ID)

A	23.5±1.0mm
B	22.2±1.0mm
C	13.5±0.8mm
D	36.0±1.0mm
E	10.5±1.0mm
F	20±1.0mm
G	29.4±1.0mm
H	13±0.8mm

	
<b>Title:</b> Ferriti Core / Ferriti Ring for round cable 13 mm 2 pieces black	
<b>Dat</b>	2024 / 07 / 19
<b>Unit</b>	mm
<b>Projection</b>	
<b>Rev</b>	A
<b>Item no.</b>	80948
<b>Barcode</b>	4043619809486
<b>File No.</b>	88417